



BITUMEN 60/70

Analysis	Unit	Limit	Test Method
Density at 25°C	Kg/m ³	1010-1060	ASTM-D71 or D3289
Penetration at 25°C	mm/10	60/70	ASTM-DS
Softening point	°C	49/56	ASTM-D36
Ductility at 25°C	cm.	100min.	ASTM-D113
Loss on Heating	%wt.	0.2 max.	ASTM-D6
Drop in penetration after Heating	%	20 max.	ASTM- D5
Flash point	°C	250min.	ASTM-D92
Solubility in CS ₂	%wt.	99.5min	ASTM-D2042
Spot Test	---	Negative	A.A.S.H.O.T 102
Viscosity @ 60°C	P	2000±400	ASTM-D2171
Viscosity @ 135°C	cSt	300 min	ASTM-D2170
Test on Residue From Thin Film Oven Test (ASTM-D1754)			
Retained Penetration after (T.F.O.T), %	%	54 min	ASTM-D5
Ductility, (25°C), 5 cm/min, cm after TFOT	cm	50	ASTM-D113
Viscosity @ 60°C	P	10000 max	ASTM-D2171

آدرس: تهران، خیابان ولیعصر، نرسیده به بزرگراه نیایش، خیابان

بهرامی، پلاک ۷۴، طبقه ۵

نماینده: ۸۸۶۵۱۷۰۷

تلفن: ۸۸۶۵۱۷۰۴-۶

Address: 5th Floor, Bahrami st, Valiasr st, Tehran

Tell: 88651704-6

Fax: 8861707